



ADS GEOSYNTHETICS 0451T NONWOVEN GEOTEXTILE

Scope

This specification describes ADS Geosynthetics 4.2 oz (0451T) nonwoven geotextile.

Filter Fabric Requirements

ADS Geosynthetics 4.2 oz (0451T) is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. ADS Geosynthetics 4.2 oz (0451T) resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. ADS Geosynthetics 4.2 oz (0451T) conforms to the physical property values listed below:

Filter Fabric Properties

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Grab Tensile	ASTM D 4632	lbs (kN)	120 (0.533)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	50 (0.222)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	310 (1.38)
Permittivity*	ASTM D 4491	sec ⁻¹	1.7
Water Flow*	ASTM D 4491	gpm/ft ² (l/min/m ²)	135 (5500)
AOS*	ASTM D 4751	US Sieve (mm)	70 (0.212)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	3.0/4.0/5.0/6.25/7.5/12.5/15 x 360
Square Yards Per Roll	120/160/200/250/300/500/600
Estimated Roll Weight – lbs	36/38/60/76/90/152/180

* At the time of manufacturing. Handling may change these properties.