

ADS GEOSYNTHETICS ADS BX374GGS BIAXIAL GEOGRID PRODUCT SPECIFICATION:

Product Type: Integrally Formed Biaxial Geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive Mechanical Interlock
Primary Applications: Base Reinforcement, Subgrade Improvement

Product Properties:

INDEX PROPERTIES	UNIT	MD VALUES ¹	XMD VALUES ¹
Aperture Dimensions ²	mm (in)	66 (2.6)	66 (2.6)
Minimum Rib Thickness ²	mm (in)	2.4 (0.09)	1.3 (0.05)
Tensile Strength @ 2% Strain ³	kN/m (lb/ft)	10.5 (719)	10.5 (719)
Tensile Strength @ 5% Strain ³	kN/m (lb/ft)	21.0 (1,439)	21.0 (1,439)
Ultimate Tensile Strength ³	kN/m (lb/ft)	30.0 (2,055)	30.0 (2,055)
STRUCTURAL INTEGRITY			
Junction Efficiency ⁴	%	93	93
Flexural Stiffness ⁵	mg-cm	2,000,000	2,000,000
Aperture Stability ⁶	m-N/deg	0.75	0.75
Durability			
Resistance to Long Term Degradation ⁸	%	100	
Resistance to UV Degradation ⁹	%	100	
DIMENSIONS AND DELIVERY			
The biaxial geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 3.9 meters (12.9 feet) in width and 50.0 meters (164 feet) in length.			

Notes:

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. True resistance to elongation when initially subjected to a load determined in accordance with ASTM D6637-10 without deforming test materials under load before measuring such resistance or employing "secant" or "offset" tangent methods of measurement so as to overstate tensile properties.
4. Load transfer capability determined in accordance with ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
5. Resistance to bending force determined in accordance with ASTM D7748-12.
6. In-place torsional rigidity measured by applying a moment to the central junction of a 225mm x 225mm specimen restrained at its perimeter in accordance with GRI-GG9.
7. Resistance to loss of load capacity or structural integrity when subjected to mechanical installation stress in clayey sand (SC), well-graded sand (SW), and crushed stone classified as poorly graded gravel (GP). The geogrid shall be sampled in accordance with ASTM D5818-06 and load capacity shall be determined in accordance with ASTM D6637-01.
8. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
9. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.